




## AUSTRALIAN JOURNAL OF BASIC AND APPLIED SCIENCES

ISSN:1991-8178 EISSN: 2309-8414  
Journal home page: www.ajbasweb.com



### Synthesis and Characterization of Ag Metal Nanoparticles Prepared in Different Solutions Using Nd-YAG Pulsed Laser

S. M. Thahab

University of Kufa, Electronics and Communication Department, Faculty of Engineering, 21 Najaf, IRAQ

**Address For Correspondence:**

S. M. Thahab, University of Kufa, Electronics and Communication Department, Faculty of Engineering, 21 Najaf, IRAQ

**ARTICLE INFO**

**Article history:**

Received 18 December 2016

Accepted 16 February 2017

Available online 25 February 2017

**Keywords:**

Nanoparticles; Absorption; Nd-YAG laser; Laser ablation

**ABSTRACT**

Naonosecond Nd:YAG laser was utilized as a part of the vast majority of tests achieved up today. Aside from the vitality of laser pulse energy, the aftereffects of laser removal in fluid stage rely on upon numerous other test parameters: laser wavelength, time of removal investigation, blending conditions and centering conditions. The Exact impact of a significant number of these components is not clear up today. In the event that most of the takes a shot at laser removal of fluid was performed in immaculate water (the fundamental inspiration for these works is SERS application or in watery arrangements, a few specialists made their trials in various natural solvents. Silver (Ag) nanoparticles (NPs) were synthesized by pulsed (Q-switched, 1064 doubled frequency-Nd: YAG). The laser ablation of silver metal plates has been performed by immersing these metal plates in deionised water DDW and NaCL solvent. The pulsed laser ablation in liquids (PLAL) process preformed with different laser shots such as 15 and 30 pulses and laser pulse energy of(600-900) mJ and liquid depth is 8 mm. The formation efficiency of PLAL process was quantified in term of the absorption spectrum peaks. The absorption spectra Ag shows a sharp and single peak around 412 nm indicates the production of pure and spherical Ag NPs with an average size in the range of (5- 20) nm. There is a simultaneous possibility of on-line observation of the nanoparticles formation via measuring the variation in nanoparticles absorption at the peaks observed. Changing the way of the fluid environment is a simple and flexible way to control the size appropriation and strength of silver colloidal nanoparticles.

**INTRODUCTION**

Silver and gold nanoparticles Ag NPs have been widely used during the past few years in various applications, such as biomedicine, biosensor, and catalysis (Mafune et.al.2000). Silver nanoparticles are of interest in light of the spellbinding properties which can be joined into antimicrobial applications, biosensor materials, composite strands, mending things, and electronic segments (Kim et al. 2005).

The removal effectiveness and the attributes of created nanosilver particles rely on many components, for example, the wavelength of the laser impinging the metallic concentrate on, the length of the laser beats (in the nanosecond organization), the laser fluence, the expulsion time traverse and the intense liquid medium, with or without the closeness of surfactants (Kim et al. 2005; Tarasenko et al. 2006; Kawasaki and Nishimura 2006). One vital preferred standpoint of laser removal procedure contrasted with different strategies for generations of metal colloids is the nonattendance of compound reagents in game plans. Thus, faultless and uncontaminated metal colloids for further applications can be set up by this technique (Tsuji et al. 2002). Silver nanospheroids (20-50 nm) were set up by laser evacuation in water with femtosecond laser heartbeats at 800 nm (Tsuji et al.

Open Access Journal

Published BY AENSI Publication

© 2017 AENSI Publisher All rights reserved

This work is licensed under the Creative Commons Attribution International License (CC BY).

<http://creativecommons.org/licenses/by/4.0/>



Open Access

**To Cite This Article:** S. M. Thahab., Synthesis and Characterization of Ag Metal Nanoparticles Prepared in Different Solutions Using Nd-YAG Pulsed Laser. *Aust. J. Basic & Appl. Sci.*, 11(2): 16-20, 2017

2003). The improvement viability and the degree of colloidal particles were differentiated and those of colloidal particles organized by nanosecond laser beats.

Few physical and substance techniques have been utilized for incorporating and settling silver and gold nanoparticles (Suji *et al.* 2002). The most prominent compound methodologies, including synthetic lessening utilizing an assortment of natural and inorganic decreasing operators, electrochemical systems, physico-concoction diminishment, and radiolysis are generally used in the blend of silver nanoparticles. Starting late, nanoparticle amalgamation has been among the most captivating consistent areas of demand, and there is creating insights with respect to deliver nanoparticles using actual altruistic techniques (green science). Green amalgamation approaches join mixed valence polyoxometalates, polysaccharides, Tollens, normal, and the enlightenment system which has inclinations over conventional techniques incorporating engineered administrators associated with natural noxious quality. (Dowling *et al.* 2003)

One critical preferred standpoint of the laser removal system contrasted with different strategies for generations of metal colloids is the nonappearance of substance reagents in arrangements. Thusly, unadulterated and uncontaminated metal colloids for further applications can be set up by this procedure (Kabashin and Meunier 2003). In this research silver and gold nanoparticles have been set up by physical blend approach. Most vital physical methodologies incorporate dissipation buildup and laser ablation. The ablation effectiveness and the attributes of delivering nanosilver particles rely on many components, for example, the wavelength of the laser impinging the metallic focus on, the span of the laser beats, the laser fluence, the removal time term and the successful fluid medium, with or without the nearness of surfactants.

The point of this work is to exhibit the impacts of encompassing particles on nucleation, development instruments and size conveyance. Changes in the fluid environment utilized as a part of laser removal give a basic and adaptable strategy to adjust the properties of nanoparticles.


#### Experimental Details:

Silver nanoparticles were set up by laser removal of a silver target. The objectives with 3mm thickness and a faultlessness of 99.99 were washed with ethanol and deionized water to clear trademark blends in an ultrasonic cleaner. The cleaned target was made plans to the base of a glass vessel stacked with 50 cc of the strategy. Deionised water and NaCl orchestrate (2.0 M) were used as the liquid environment for laser launch.

The sample surface was kept at 10 mm. In the midst of laser clearing, the specimen was swing physically to ensure uniform expulsion and to keep up a basic segment from a Completing effect. Nd:YAG laser with a focal wavelength of 1064 nm and heartbeat length of 8ns was used in removal handle. The laser was working at a wealth rate of 6 Hz. The Gaussian laser shaft was secured by a procedure of optical segments and gave at the standard scene to the surface of the goal. After 5min of flight the UV-Vis annihilation spectra of silver colloid was in a flash measured by a spectrophotometer (Shimadzu UV-1650 PC). The surface morphology of the particles was examined by electron microscopy (INSPECT-550) and SPM AA3000 AFM supply by Angstrom co.


## RESULTS AND DISCUSSION

Fig. 1a and bdemonstrates SEM picture and EDX of silver nanoparticles arranged in deionised water individually. As can be evidently observed, no aggregate happened and the size scattering is slim with an ordinary size of (5-20) nm. In all media as shown up in SEM pictures, the silver nanoparticles are circular fit as a fiddle. Likewise, expanding of the elimination spectra in NaCL (fig.5) is identified with the wide size appropriation of the particles as affirmed by SEM pictures. These perceptions recommend that the size appropriation and strength of nanoparticles rely on upon the way of the encompassing fluid situations amid removal (Pyatenco *et al.* 2004, Tsuji *et al.* 2002).




**Fig. 1:** SEM image (a) and EDX chart (b) of Ag NP on silicon substrate

The sizes and morphology of Nano-Ag was analyzed by utilizing a transmission electron magnifying instrument (TEM). The outcomes demonstrate that the Nano-Ag was in a round shape and has a normal size of 10 nm (Fig. 2). Fig.3 demonstrates AFM pictures of Ag NPs. An expansion in the development rate brings about a more extensive size appropriation with a more noteworthy normal size of nano-molecule which is around 10 nm. High polar atoms, for example, NaCl or little size polar particles, for example, DDW limited the development instruments. As mentioned above, in NaCl in light of the high dipole of encompassing atoms, the covering of solid electrical twofold layers makes an adequate electrostatic horrendous drive between nanoparticles. Consequently, no total and precipitation happen and the colloidal arrangement is steady (Tilaki, *et al.* 2006, Tarasenko *et al.* 2006)




**Fig. 2:** TEM image of Ag NP on silicon substrate




**Fig. 3:** AFM images of Ag NPs(a) volume percentage (b) 3D image of AgNPs

optical properties of AgNPs were considered by optical estimations of fluids that contained silver nanoparticles as appeared in fig.4. All estimations were performed rapidly after the arrangement of nanoparticles. In the water, optical decimation, it stays unaltered despite taking following a few days. Because of the development system, the greatest of the optical annihilation at various circumstances after removal showed some red shift of peak wavelength. (Tilaki *et al.* 2006, Tsuji *et al.* 2002).




**Fig. 4:** The absorbance spectrum of Ag NP in DDW a pulse laser number of 15 pulse and laser energy of 600 mJ.

Figure 5 demonstrates the optical absorption spectra of silver nanoparticles on NaCl arrangement at a peak wavelength of 410 nm is because of surface plasmon. The position and number of the pinnacles are distinguished by the size, shape and the material kind of the nanoparticles. Expanding of the optical termination identified with the size conveyance and accumulation of the nanoparticles. Figure 6 indicates optical absorption spectra of silver nanoparticles arranged at the distinctive number of laser pulses in the range of 15 to 60 p. The spectra show assimilation crests at unmistakable wavelengths situated at 404 and 413 nm individually (Tsuji *et al.* 2002)




**Fig. 5:** The absorbance spectrum of of Ag NP in NaCl a pulse laser number of 15 pulse and laser energy of 600 mJ.



**Fig. 6:** The absorbance spectrum of of Ag NP in NaCl as a function a pulse laser number of ( 15, 30, 60 p) and laser energy of 600 mJ.

Figure 7 shows the optical absorbance spectra of Ag NPs is sharp in DDW solution despite the fact that the width of the spectra increments somewhat in NaCl arrangement. A development in the progression rate achieves a more broad size allocation with a more conspicuous typical size of nanoparticle. The above results clear up the effects of the enveloping particles on advancement segments remembering the true objective to explain the reliance of size, optical properties and soundness of colloidal reactions for the cutoff of the fluid circumstances (Resano *et al.* 2015)



**Fig. 7:** The absorbance spectrum of of Ag NP in NaCl and DDW at a pulse laser number of 15p laser energy of 600 mJ.

### Conclusions:

The size, optical properties and morphology of silver nanoparticles was researched in different liquid mediums. Silver nanoparticles was set up in NaCl, and deionised water media. Silver nanoparticles in a deionised water showed a slim size scattering and a wavelength of most prominent optical demolition at 408nm. It was observed that the Ag colloidal plan was consistent and no precipitation appears. In NaCl areasonably restrict assess flow with and a wavelength of most prominent optical disposal at 410 nm were gotten. High polar atoms give a strong, incorporating electrical twofold layer, which maintains a strategic distance from improvement, gathering and precipitation. In this way changing the strategy for the fluid environment is a fundamental and adaptable approach to manage,control the size dispersal and security of colloidal silver nanoparticles. Transmission electron microscopy was used in the depiction of the size and condition of particles. Optical end spectra were furthermore used to gag and study the optical properties from 300 to 900 nm. Colloidal plan is relentless and no precipitation appears. In deionized water a somewhat limit measure appropriation was observed. Nucleation, development and conglomeration components are identified with the extremity of the

fluid environment. High polar atoms give a solid, encompassing electrical twofold layer, which counteracts development, conglomeration and precipitation. Subsequently changing the way of the fluid environment is a simple and flexible way to control the size appropriation and strength of silver colloidal nanoparticles.

#### ACKNOWLEDGEMENT

The authors would like to acknowledge the assistance offered by *NAMRU* in Faculty of Engineering University of Kufa /IRAQ

#### REFERENCES

- Dowling, D.P., A.J. Betts, C. Pope, M.L. McConnell, R. Eloy, M.N. Artnauld, 2003. Anti-bacterial silver coatings exhibiting enhanced activity through the addition of platinum. *Surf. Coat. Technol.*, 637: 163-164.
- Kabashin, A.V., M. Meunier, 2003. Synthesis of colloidal nanoparticles during femtosecond laser ablation of gold in water. *J Appl Phys.*, 94: 7941-7944.
- Kawasaki, M. and N. Nishimura, 2006. 1064-nm laser fragmentation of thin Au and Ag flakes in acetone for highly productive pathway to stable metal nanoparticles. *Appl Surf Sci.*, 253: 2208-2216.
- Kim, Y.H., D.K. Lee, Y.S. Kang, 2005. Synthesis and characterization of Ag and Ag-SiO<sub>2</sub> nanoparticles. *Colloid. Surf. A: Physicochem. Eng Aspects*, 273: 257-258.
- Kim, S., B. Yoo, K. Chun, W. Kang, J. Choo, M. Gong and S. Joo, 2005. Catalytic effect of laser ablated Ni nanoparticles in the oxidative addition reaction for a coupling reagent of benzylchloride and bromoacetonitrile. *J Mol Catal A: Chem*, 226: 231-234.
- Mafune, F., J. Kohno, Y. Takeda, T. Kondow, H. Sawabe, 2000. Formation and size control of silver nanoparticles by laser ablation in aqueous solution. *J Phys Chem B.*; 104: 9111-9117.
- Pyatenco, A., K. Shimokawa, M. Yamaguchi, O. Nishimura, M. Suzuki, 2004. Synthesis of silver nanoparticles by laser ablation in pure water. *Appl. Phys. A* 79: 803.
- Resano, G., Y. Battie, A. Koch, A. En Naciri and N. Chaou, 2015. Influence of the laser light absorption by the colloid on the properties of silver nanoparticles produced by laser ablation in stirred and stationary liquid. *Journal of Applied Physics*, 117.
- Suji, T., K. Iryo, N. Watanabe, M. Tsuji, 2002. Preparation of silver nanoparticles by laser ablation in solution: influence of laser wavelength on particle size. *Appl Surf Sci.*, 202: 80-85.
- Tarasenko, N., A. Butsen, E. Nevar and N. Savastenko, 2006. Synthesis of nanosized particles during laser ablation of gold in water. *Appl Surf Sci.*, 252: 4439-4444.
- Tilaki, R.M., A. Iradj Zad, S.M. Mahdavi, 2006. Stability, size and optical properties of silver nanoparticles prepared by laser ablation in different carrier media. *Applied Physics A*, 84(1): 215-219.
- Tsuji, T., K. Iryo, N. Watanabe and M. Tsuji, 2002. Preparation of silver nanoparticles by laser ablation in solution: influence of laser wavelength on particle size. *Appl Surf Sci.*, 202: 80-85.
- Tsuji, T., T. Kakita and M. Tsuji, 2003. Preparation of nano-size particle of silver with femtosecond laser ablation in water. *Applied Surface Science*, 206: 314-320.